



Test Report

No.: SZTYR060404335/TS

Date: MAY 02, 2008

Page 1 of 3

Report on 1 PIECE submitted samples said to be TENNIS BALLS

Detail of Sample Received : TENNIS BALL.

Item No. : 2 5"

Supplier :

Country of Origin : CHINA

Labeled Age Grading : NOT STATED

Requested test Age Grading : FOR ALL AGES

Test Age Grading : FOR ALL AGES

Sample Receiving Date : APR 20, 2008

Testing Period : APR 21, 2008 TO APR 25, 2008

Y

Test Requested

For compliance with the European Standard on Safety of Toys :-

- EN71 Part 1:1998+A1:2001+A2: 2002+A4:2004+A5:2000+A6:2002+A7:2002+A8:2003+A9:2004+A10:2004+A11:2004 – Mechanical and Physical Properties
- EN71 Part 2:2003 – Flammability of Toys
- EN71 Part 3:1994 +A1:2000 – Migration of Certain Elements

Result


Pass (Except Clause 7.1)


Pass

Pass

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
SGS-CSTC Ltd.


Zhang Wei, Merry
Supervisor
HOKLAS Approved Signatories


Li Ying, Susan
Section Manager
HOKLAS Approved Signatories

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation. This report shall not be reproduced unless with prior written approval from this laboratory.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days only. This Test Report shall not be reproduced except in full, without written approval of the Company.





Test Report

No.: SZTYR060404335/TS

Date: MAY 02, 2008

Page 2 of 3

Results :

European Standard on Safety of Toys

- Mechanical and Physical Properties

AS SPECIFIED IN EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 1 : 1998 (includes amendment A1:2001, A2:2002, A4:2004, A5:2000, A6:2002, A7:2002, A8:2003, A9:2004, A10:2004, A11:2004).

Clause	Description	Result
4	General requirements	
4.1	Material (by visual assessment).....	Pass
4.7	Edges	Pass
4.8	Points and Wires	Pass
4.22	Small balls	Pass
5	Toys intended for children under 36 months	
5.1	General requirements:	
5.1a	Small part requirement on toys & removable Components (Test method 8.2)	Pass
5.1b	Torque test (Test method 8.3)	Pass
	Tension test (Test method 8.4)	Pass
	Drop test (Test method 8.5)	Pass
	Impact test (Test method 8.7)	Pass
	Sharp edge (Test method 8.11)	Pass
	Sharp point (Test method 8.12)	Pass
5.1f	Splinters	Pass
5.9	Shape and size of certain toys	Pass
5.11	Small balls.....	Pass
7	Warnings and instructions for use	
7.1	General Requirements	See Remark
	(Remark : It is drawn to your attention that the name and address of importer in EEC country and the advice statement for keeping relevant information together with CE-marking should appear as specified in clause 7.1 of this standard.)	

- Flammability of Toys

AS SPECIFIED IN EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 2 : 2003.

Clause	Description	Result
4.1	General Requirements	Pass

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation. This report shall not be reproduced unless with prior written approval from this laboratory.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days. This Test Report shall not be reproduced except in full, without written approval of the Company.



4/F, Oyster Building, Zhongkang Road, Shaomelin, Shenzhen, China

T (85-755)83114753 F (86-755)83116790

www.cn.sgs.com
e sgs.china@sgs.com

Member of the SGS Group (SGS SA)



Test Report

No.: SZTYR060404335/TS

Date: MAY 02, 2008

Page 3 of 3

- Migration of Certain Elements

AS SPECIFIED IN EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 3 : 1994 (INCLUDES AMENDMENT A1:2000) - MIGRATION OF CERTAIN ELEMENTS. ANALYSIS WAS PERFORMED BY INDUCTIVELY COUPLED PLASMA ATOMIC EMISSION SPECTROMETER.

Element	1	2	Limit
Soluble Lead (Pb)	< 5	< 5	90 mg/kg
Soluble Antimony (Sb)	5	< 5	60 mg/kg
Soluble Arsenic (As)	< 5	< 5	25 mg/kg
Soluble Barium (Ba)	< 10	121	1000 mg/kg
Soluble Cadmium (Cd)	< 5	< 5	75 mg/kg
Soluble Chromium (Cr)	< 5	< 5	60 mg/kg
Soluble Mercury (Hg)	<6.7	<6.7	60 mg/kg
Soluble Selenium (Se)	< 10	< 10	500 mg/kg

Specimen Description:

1. White felt
2. White rubber

- < = Less than
- Results shown are of the adjusted analytical results.
- This report has been checked and approved by SGS-CSTC Standards Technical Services Co., Ltd. and the tests are conducted in Yangzhou Import & Export Toy Inspection Institute of the People's Republic of China with Accreditation Number Q72 (Report Number 3210/HB61179).

- N.B. : - Only applicable clauses were shown.
 - Photo Appendix is included.

*** End of Report ***

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results show in this report were determined by this laboratory in accordance with its terms of accreditation. This report shall not be reproduced unless with prior written approval from this laboratory.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days. This Test Report shall not be reproduced except in full, without written approval of the Company.



4/F, Oyster Building, Zhongtang Road, Shanghai, P.R. China

Tel: (86-755) 83114568 Fax: (86-755) 83106190

www.cn.sgs.com
e: sgs.china@sgs.com

Member of the SGS Group (SGS, SAI)



Test Report

No.: SZTYR060404335/TS

Date: MAY 02, 2008

Page 3 of 3

- Migration of Certain Elements

AS SPECIFIED IN EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 3 : 1994 (INCLUDES AMENDMENT A1:2000) - MIGRATION OF CERTAIN ELEMENTS. ANALYSIS WAS PERFORMED BY INDUCTIVELY COUPLED PLASMA ATOMIC EMISSION SPECTROMETER.

Element	1	2	Limit
Soluble Lead (Pb)	< 5	< 5	90 mg/kg
Soluble Antimony (Sb)	5	< 5	60 mg/kg
Soluble Arsenic (As)	< 5	< 5	25 mg/kg
Soluble Barium (Ba)	< 10	121	1000 mg/kg
Soluble Cadmium (Cd)	< 5	< 5	75 mg/kg
Soluble Chromium (Cr)	< 5	< 5	60 mg/kg
Soluble Mercury (Hg)	<6.7	<6.7	60 mg/kg
Soluble Selenium (Se)	< 10	< 10	500 mg/kg

Specimen Description:

1. Yellow felt
2. White rubber

- < = Less than
- Results shown are of the adjusted analytical results.
- This report has been checked and approved by SGS-CSTC Standards Technical Services Co., Ltd. and the tests are conducted in Yangzhou Import & Export Toy Inspection Institute of the People's Republic of China with Accreditation Number 072 (Report Number 3210/HB61179).

- N.B. : - Only applicable clauses were shown.
 - Photo Appendix is included.

*** End of Report ***

Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation. This report shall not be reproduced unless with prior written approval from this laboratory.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days. This Test Report shall not be reproduced except in full, without written approval of the Company.



4/F, Center Building, Zhongkang Road, Shangmeilin, Shenzhen, China

T (86-755)83114358 F (86-755)83165190

www.cn.sgs.com
e sgs.china@sgs.com

Member of the SGS Group (SGS SA)